

ABS Glass Fiber Composite - ABS+10%G/F
Grade: A6010N,A6010B

項目 Property	單位 Units	方法 Test Method	數值	數值
			Value A6010N	Value A6010B
Specific Density 比重		D-792	1.12	1.12
Filler Content 填充物含量	%		10%	10%
Tensile Strength 抗張強度	kgf/cm ²	D-638	600	550
Tensile Elongation 延伸率	%	D-638	3.5	4
Flexural Strength 彎曲強度	kgf/cm ²	D-790	820	820
Flexural Modulus 彎曲模數	kgf/cm ²	D-790	30400	30400
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	9.5	9.5
Melt Index 融溶指數	g/10min	D-1238	9	9
Shrinkage 收縮率	%	D-955	0.2~0.4	0.2~0.4
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	92	92
Rockwell Hardness 洛氏硬度	R-scale	D-785	R115	R115
Description 產品描述			10%玻纖強化本色	10%玻纖強化黑色

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHEIN TAIWAN. R.O.C.