

ABS Glass Fiber Composite - ABS+30%G/F
Grade: A6030N,A6030B

項目 Property	單位 Units	方法 Test Method	數值	數值
			Value A6030N	Value A6030B
Specific Density 比重		D-792	1.3	1.3
Filler Content 填充物含量	%		30%	30%
Tensile Strength 抗張強度	kgf/cm ²	D-638	1100	950
Tensile Elongation 延伸率	%	D-638	2.7	3
Flexural Strength 彎曲強度	kgf/cm ²	D-790	1300	1080
Flexural Modulus 彎曲模數	kgf/cm ²	D-790	68000	59850
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	7.5	7.5
Melt Index 融溶指數	g/10min	D-1238	4.5	4.5
Shrinkage 收縮率	%	D-955	0.1~0.3	0.1~0.3
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	101	101
Rockwell Hardness 洛氏硬度	R-scale	D-785	R117	R117
Description 產品描述			30%玻纖強化本色	30%玻纖強化黑色

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHEIN TAIWAN. R.O.C.