



Strategy Planning of Plastic Material

## PA6 Carbon/Glass Fiber Composite - PA6+ Carbon Black Grade: NC105B

項目 Property	單位 Units	方法 Test Method	數值 Value
Specific Density	比重	D-792	1.19
Filler Contant	填充物含量	%	-
Tensile Strength	抗張強度	kgf/c m <sup>2</sup>	600
Tensile Elongation	延伸率	%	35
Flexural Strength	彎曲強度	kgf/c m <sup>2</sup>	970
Flexural Modulus	彎曲模數	kgf/c m <sup>2</sup>	26000
Izod impact Strength	衝擊強度	kgf cm/cm	14
1/8" bar with notched	(有缺口)		
Melt Index	融溶指數	g/10min	-
Shrinkage	收縮率	%	-
Dercription	產品描述	-	導電炭黑補強 Carbon Black reinforce

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE, LIN KOW SHARUNG TAIPEI SHEIN TAIWAN, R.O.C.