



Strategy Planning of Plastic Material

PA6 Mineral Fiber Composite - PA6+40%MF Grade: NR140M

項目 Property	單位 Units	方法 Test Method	數值 Value
Specific Density	比重	D-792	1.57
Filler Contant	填充物含量	%	40%
Tensile Strength	抗張強度	kgf/c m ²	850
Tensile Elongation	延伸率	%	3
Flexural Strength	彎曲強度	kgf/c m ²	1400
Flexural Modulus	彎曲模數	kgf/c m ²	60000
Izod impact Strength	衝擊強度	kgf cm/cm	12
1/8" bar with notched	(有缺口)		
Melt Index	融溶指數	g/10min	-
Shrinkage	收縮率	%	-
H.D.T. (66 Psi)	熱變形溫度	°C	190
Rockwell Hardness	洛氏硬度	R-scale	D-785 R120
Dercription	產品描述		40%礦纖 低翹曲性

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHEIN TAIWAN, R.O.C.