

PA6 Glass Fiber Composite - PA6+45%GF
Grade: NR145GN,NR145GB

項目 Property	單位 Units	方法 Test Method	數值 Value	數值 Value
			NR145GN	NR145GB
Specific Density 比重		D-792	1.5	1.5
Filler Contant 填充物含量	%		45%	45%
Tensile Strength 抗張強度	kgf/c m ²	D-638	2150	2100
Tensile Elongation 延伸率	%	D-638	4	4
Flexural Strength 彎曲強度	kgf/c m ²	D-790	3000	2900
Flexural Modulus 彎曲模數	kgf/c m ²	D-790	100000	99500
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	18	18
Melt Index 融溶指數	g/10min	D-1238	10	10
Shrinkage 收縮率	%	D-955	0.3-0.6	0.3-0.6
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	240	240
Rockwell Hardness 洛氏硬度	R-scale	D-785	120	120
Dercription 產品描述			45%玻纖強 化本色高 剛性	45%玻纖 強化黑色 高剛性

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHEN TAIWAN, R.O.C.