

PA66 Glass Fiber Composite - PA66+20%GF
Grade: NR220GN,NR220GB

項目 Property	單位 Units	方法 Test Method	數值 Value	
			NR220GN	NR220GB
Specific Density 比重		D-792	1.28	1.28
Filler Contant 填充物含量	%		20%	20%
Tensile Strength 抗張強度	kgf/c m ²	D-638	1500	1450
Tensile Elongation 延伸率	%	D-638	5	5
Flexural Strength 彎曲強度	kgf/c m ²	D-790	2230	2180
Flexural Modulus 彎曲模數	kgf/c m ²	D-790	65000	65000
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	7	7
Melt Index 融溶指數	g/10min	D-1238	-	-
Shrinkage 收縮率	%	D-955	0.5-0.9	0.5-0.9
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	250	250
Rockwell Hardness 洛氏硬度	R-scale	D-785	120	120
Dercription 產品描述		20%GF High rigidity	20%玻纖本 色 剛性	20%玻纖 黑色 高剛性

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHBIN TAIWAN, R.O.C.