

PA66 Glass Fiber Composite - PA66+30%GF
Grade: NR230GN,NR230GB

項目 Property	單位 Units	方法 Test Method	數值 Value	
			NR230GN	NR230GB
Specific Density 比重		D-792	1.36	1.36
Filler Contant 填充物含量	%		30%	30%
Tensile Strength 抗張強度	kgf/c m ²	D-638	1800	1800
Tensile Elongation 延伸率	%	D-638	4	4
Flexural Strength 彎曲強度	kgf/c m ²	D-790	2550	2500
Flexural Modulus 彎曲模數	kgf/c m ²	D-790	78000	77000
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	14	14
Melt Index 融溶指數	g/10min	D-1238	-	-
Shrinkage 收縮率	%	D-955	0.2-0.7	0.2-0.7
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	252	252
Rockwell Hardness 洛氏硬度	R-scale	D-785	120	120
Dercription 產品描述		30%GF High rigidity	30%玻纖本 色 高剛性	30%玻纖 黑色 高剛性

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHEN TAIWAN, R.O.C.