

PA66 Glass Fiber Composite - PA66+45%GF
Grade: NR245GN,NR245GB

項目 Property	單位 Units	方法 Test Method	數值 Value	
			NR245GN	NR245GB
Specific Density 比重		D-792	1.5	1.5
Filler Contant 填充物含量	%		45%	45%
Tensile Strength 抗張強度	kgf/c m ²	D-638	2100	2100
Tensile Elongation 延伸率	%	D-638	3.3	3.3
Flexural Strength 彎曲強度	kgf/c m ²	D-790	3050	3000
Flexural Modulus 彎曲模數	kgf/c m ²	D-790	120000	120000
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	15	15
Melt Index 融溶指數	g/10min	D-1238	-	-
Shrinkage 收縮率	%	D-955	0.1-0.4	0.1-0.4
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	253	253
Rockwell Hardness 洛氏硬度	R-scale	D-785	121	121
Dercription 產品描述		45%GF High rigidity	45%玻纖本色高剛性	45%玻纖本色高剛性

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHBIN TAIWAN, R.O.C.