



Strategy Planning of Plastic Material

PA66/6 Glass Fiber Composite - PA66/6+15%GF Grade: NR315GN

項目 Property	單位 Units	方法 Test Method	數值 Value
Specific Density 比重		D-792	1.23
Filler Contant 填充物含量	%		15%
Tensile Strength 抗張強度	kgf/c m ²	D-638	970
Tensile Elongation 延伸率	%	D-638	6
Flexural Strength 彎曲強度	kgf/c m ²	D-790	1300
Flexural Modulus 彎曲模數	kgf/c m ²	D-790	22300
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	9
Melt Index 融溶指數	g/10min	D-1238	-
Shrinkage 收縮率	%	D-955	0.6-1.0
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	225
Rockwell Hardness 洛氏硬度	R-scale	D-785	R117
Dercription 產品描述		15%GF High rigidity	15%玻纖 本色 高剛性

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後港52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHEIN TAIWAN, R.O.C.