

**PA6 GF/Super Tough Composite -PA6+15%GF Good Impact**  
**Grade: NT115GN,NT115GB**

項目 Property	單位 Units	方法 Test Method	數值 Value	
			NT115GN	NT115GB
Specific Density 比重		D-792	1.19	1.19
Filler Contant 填充物含量	%		15%	15%
Tensile Strength 抗張強度	kgf/c m <sup>2</sup>	D-638	750	730
Tensile Elongation 延伸率	%	D-638	5	5
Flexural Strength 彎曲強度	kgf/c m <sup>2</sup>	D-790	1000	940
Flexural Modulus 彎曲模數	kgf/c m <sup>2</sup>	D-790	33000	31000
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	21	20
Melt Index 融溶指數	g/10min	D-1238	-	-
Shrinkage 收縮率	%	D-955	-	-
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	190	190
Rockwell Hardness 洛氏硬度	R-scale	D-785	R118	R118
Dercription 產品描述			15%玻纖強 化本色 耐衝擊	15%玻纖強 化黑色 耐衝擊

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE LIN KOW SHARUNG TAIPEI SHEIN TAIWAN, R.O.C.