

PA6 GF/Super Tough Composite -PA6+30%GF Good Rigidity Grade: NT130GN,NT130GB

項目 Property	單位 Units	方法 Test Method	數值 Value	
			NT130GN	NT130GB
Specific Density 比重		D-792	1.33	1.33
Filler Contant 填充物含量	%		30%	30%
Tensile Strength 抗張強度	kgf/c m ²	D-638	1200	1100
Tensile Elongation 延伸率	%	D-638	4	4
Flexural Strength 彎曲強度	kgf/c m ²	D-790	1550	1420
Flexural Modulus 彎曲模數	kgf/c m ²	D-790	56000	54000
Izod impact Strength 衝擊強度 1/8" bar with notched (有缺口)	kgf cm/cm	D-256	16.6	16.2
Melt Index 融溶指數	g/10min	D-1238	-	-
Shrinkage 收縮率	%	D-955		
H.D.T. (66 Psi) 熱變形溫度	°C	D-648	200	200
Rockwell Hardness 洛氏硬度	R-scale	D-785	R119	R119
Dercription 產品描述			30%玻纖 本色 高剛性 耐衝擊	30%玻纖 黑色 高剛性 耐衝擊

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO.,L.T.D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後港52-16號 NO.52-16 HOU HU HU-PEI VILLAGE .LIN KOW SHARUNG TAIPEI SHEN TAIWAN. R.O.C.