

**PP Mineral Fiber Composite - PP+ 40%TALC+Antistatic
Grade: PT4oAN-283**

項目 Property	單位 Units	方法 Test Method	數值 Value
Specific Density	比重	D-792	1.44
Filler Contant	填充物含量	%	43%
Tensile Strength	抗張強度	kgf/cm ²	300
Tensile Elongation	延伸率	%	8
Flexural Strength	彎曲強度	kgf/cm ²	500
Flexural Modulus	彎曲模數	kgf/cm ²	27500
Izod impact Strength 1/8" bar with notched	衝擊強度 (有缺口)	kgf cm/cm	6
Melt Index	融溶指數	g/10min	11
Shrinkage	收縮率	%	0.9~1.0
H. D. T. (66 Psi)	熱變形溫度	°C	135
Rockwell Hardness	洛氏硬度	R-scale	103
Surface Resistivity	表面阻抗	Ω	10 ⁹ - 10 ¹²
Dercription	產品描述	40%Talc Antistatic	40%滑石粉 補強 抗靜 電 高透光

☆上表所列數據資料僅供參考用

These property values under specific test conditions as defined in the table above are for reference only.

揚智企業有限公司 YANPLA INDUSTRIAL CO., L. T. D TEL:886-2-26039888 FAX:886-2-26039887

台北縣林口鄉湖北村後湖52-16號 NO.52-16 HOU HU HU-PEI VILLAGE .LIN KOW SHARUNG TAIPEI SHEIN TAIWAN. R.O.C.